

M382 plus / M382 S plus

Flame fused doped multi-step quartz tube



Product Overview

M382 plus is a doped (cerium oxide) flame fused quartz made from semi-synthetic grain, designed for demanding laser and lamp requirements. The tube is fabricated using the unique Heraeus multi-step process.

Key Features

- highest resistance to intense light pulses
- very low bubble content
- nearly blemish free surface
- wide range of geometries

Applications (e.g.)

- laser excitation lamp
- IPL (intense pulsed lamp)

Geometrical Data

Outer Diameter (OD) [mm]	Tolerance [mm] ¹	Wall Thickness Range [mm]
2 - ≤ 8	± 0.3	≥ 0.4 - ≤ 2.0
> 8 - ≤ 17	± 0.4	≥ 0.8 - ≤ 3.5
> 17 - ≤ 25	± 0.6	≥ 1.0 - ≤ 4.5
> 25 - ≤ 30	± 0.7	≥ 1.2 - ≤ 4.5
> 30 - ≤ 35	± 0.8	> 1.2 - ≤ 4.5
> 35 - ≤ 40	± 1.0	> 1.2 - ≤ 4.5

Wall Thickness (WT) [mm]	Tolerance [mm]	Cumulative length of bubbles ²
≥ 0.4 - ≤ 0.5	± 0.15	< 2.0 %
> 0.5 - ≤ 1.2	± 0.20	< 2.5 %
> 1.2 - ≤ 2.0	± 0.30	< 3.0 %
> 2.0 - ≤ 2.8	± 0.40	< 3.5 %
> 2.8 - ≤ 3.7	± 0.50	< 4.0 %
> 3.7 - ≤ 4.5	± 0.60	< 4.5 %

Feature	Area	Tolerance	Note
Ovality	manufactured length	< ½ OD tolerance	(e.g. ± 0.20 OD tolerance = ovality of 0.20)
Siding	manufactured length	< ½ WT tolerance	(e.g. ± 0.20 WT = siding of 0.20)
Bow	all dimensions	< 1.0mm / 1m < 1.5mm / 1m	not annealed annealed
Length	-	+ 20mm / - 0mm	snap cut ³


¹ Additional sizes and tolerances are available on request

² Bubbles < 0.5 mm length and < 0.08 mm width are not counted

³ Other cutting methods on request

Optical Properties

Typical transmission values for 2mm wall thickness



Wavelength [nm]	245	315	350	380	436	588
Transmission M382 plus [%]	28	0	10	73	92	93
Transmission M382 S plus [%]	1	0	26	80	92	93

Visual Features

Tolerance

Outside Surface Distortion	none
Surface Impurities (adherent)	none
Open Bubbles	none
Inclusions	none
Discoloration / Draw Lines	none
Devitrification	none (only for M382 S plus: ≤ 1mm, max. 5pcs.)

Chemical Properties

OH Content [ppm]	130 - 220										no change in OH content through annealing
Chemical Impurities [ppm]	Li	Na	K	Mg	Ca	Fe	Cu	Cr	Mn	Al	Ti
	0.6	0.1	0.05	0.05	0.05	0.1	0.05	0.05	0.05	8	doped

Physical Properties

Softening Temperature	~ 1660°C
Annealing Temperature	~ 1160°C
Strain Temperature	~ 1070°C
Viscosity at 1300°C	~ 11.55 dPas
Maximum Working Temperature	continuous operation ~ 1110°C short-term operation ~ 1250°C
Density	2.2 g/cm ³

CONTACT

Germany

Heraeus Quarzglas GmbH & Co. KG
Heraeus Conamic
+49 (6181) 35-6234
conamic.lampmaterials@heraeus.com
heraeus-conamic.com

USA

Heraeus Quartz North America LLC
Heraeus Conamic
+1 (240) 690-3852
conamic.lampmaterials@heraeus.com
heraeus-conamic.com

The data given here is correct as of July 2021 and is subject to change.

The Heraeus logo, Heraeus and Conamic are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved. For more information, visit www.heraeus.us/conamic-trademarks.