

Suprasil 130

Synthetic multi step quartz tube



Product Overview

Suprasil 130 is a fully synthetic fused silica with a stable OH content >100ppm. Suprasil 130 is designed for highest efficiency UV/VUV lamp applications. The tube is fabricated using the unique Heraeus multi-step process (S-ZUG).

Key Features

- highest purity
- high solarization resistance
- very low bubble content
- nearly blemish free surface
- wide range of geometries

Applications (e.g.)

- VUV low pressure lamp (185nm)
- UV/VUV sleeve

Geometrical Data

Outer Diameter (OD) [mm]	Tolerance [mm] ¹	Wall Thickness Range [mm]
7 - ≤ 17	± 0.3	≥ 0.8 - ≤ 3.5
> 17 - ≤ 25	± 0.4	≥ 1.0 - ≤ 4.5
> 25 - ≤ 30	± 0.5	≥ 1.2 - ≤ 4.5
> 30 - ≤ 35	± 0.6	> 1.2 - ≤ 4.5
> 35 - ≤ 40	± 0.8	> 1.2 - ≤ 4.5
> 40 - ≤ 45	± 1.0	≥ 1.8 - ≤ 4.5

Wall Thickness (WT) [mm]	Tolerance [mm]	Cumulative length of bubbles ²
≥ 0.8 - ≤ 1.2	± 0.2	< 2.0%
> 1.2 - ≤ 1.8	± 0.3	< 2.5%
> 1.8 - ≤ 2.5	± 0.5	< 3.0%
> 2.5 - ≤ 3.0	± 0.6	< 3.5%
> 3.0 - ≤ 4.0	± 0.8	< 4.0%
> 4.0 - ≤ 4.5	± 1.0	< 4.5%

Feature	Area	Tolerance	Note
Ovality	manufactured length	< ½ OD tolerance	
Siding	manufactured length	< ½ OD tolerance	
Bow	all dimensions	< 1.0mm / 1m < 1.5mm / 1m	not annealed annealed
Length	-	+ 20mm / - 0mm	snap cut ³


¹ Additional sizes and tolerances are available on request

² Bubbles < 0.5 mm length and < 0.08 mm width are not counted

³ Other cutting methods on request

Optical Properties

Typical transmission values for 2mm wall thickness



Wavelength [nm]	185	200	254	360
Transmission [%]	90	91	92	93

Visual Features

Tolerance

Inclusions	none
Surface Impurities (adherent)	none
Outside surface distortion	none
Discoloration	none

Chemical Properties

OH Content [ppm]	100 - 200	no change in OH content through annealing									
Chemical Impurities [ppm]	Li	Na	K	Mg	Ca	Fe	Cu	Cr	Mn	Al	Ti
	0.01	0.2	0.01	0.005	0.05	0.02	0.01	0.005	0.005	0.05	0.05

Physical Properties

Softening Temperature	~ 1600°C
Annealing Temperature	~ 1120°C
Strain Temperature	~ 1025°C
Viscosity at 1300°C	~ 11.4 dPas
Maximum Working Temperature	continuous operation ~ 950°C short-term operation ~ 1200°C
Density	2.2 g/cm ³

CONTACT

Germany

Heraeus Quarzglas GmbH & Co. KG
Heraeus Conamic
+49 (6181) 35-6234
conamic.lampmaterials@heraeus.com
heraeus-conamic.com

USA

Heraeus Quartz North America LLC
Heraeus Conamic
+1 (240) 690-3852
conamic.lampmaterials@heraeus.com
heraeus-conamic.com

The data given here is correct as of July 2021 and is subject to change.

The Heraeus logo, Heraeus, Conamic and Suprasil are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved. For more information, visit www.heraeus.us/conamic-trademarks.