




## Typical Transmission Spectrum

Sample thickness: 10 mm



## Visual Properties

Bubbles	
Bubble class (DIN 58927)	0
Maximum number of inclusions*	0

\* Bubbles and Inclusions with  $\varnothing \leq 80 \mu\text{m}$  are not counted.

## Other Properties

Abbe number	67.8
Density	2.2 g/cm <sup>3</sup>
Hardness (Mohs scale)	5.5...6.5

## Thermal Properties

Strain temperature*	1025 °C
Annealing temperature*	1120 °C
Softening temperature*	1600 °C
Coefficient of thermal expansion	$0.54 \times 10^{-6}$ (Average, K <sup>-1</sup> 0...600 °C)

\* Note that these values may vary, depending on the thermal history of the glass.

Germany  
**Heraeus Quarzglas GmbH & Co. KG**  
**Heraeus Conamic**  
 Kleinostheim, Germany  
 Phone: +49 6181 35-7444  
 conamic.basematerials.eu@heraeus.com

USA  
**Heraeus Quartz North America, LLC.**  
**Heraeus Conamic**  
 Chandler, Arizona, USA  
 Phone: +1 678 714-4306  
 conamic.basematerials.us@heraeus.com

UK  
**Heraeus Conamic UK Ltd.**  
 Wallsend, UK  
 Phone: +44 191 2598-411  
 conamic.basematerials.eu@heraeus.com

Korea  
**Heraeus Korea Corporation**  
**Heraeus Conamic Anseong Factory**  
 Miyang-myeon, Gyeonggi-do, Korea  
 Phone: +82 31 671-7601  
 conamic.basematerials.kr@heraeus.com

China  
**Heraeus ShinEtsu Quartz (China) Inc.**  
 Pudong, Shanghai, China  
 Phone: +86 21 6867 2266-809  
 conamic.basematerials.cn@heraeus.com

Japan  
**Shin-Etsu Quartz Products Co., Ltd.**  
 Shinagawa, Tokyo, Japan  
 Phone: +81 3 6737-0221  
 division3@sqp.co.jp

Taiwan  
**Heraeus Materials Technology Taiwan Ltd.**  
 Taipei, Taiwan  
 Phone: +886 2 2627-1111  
 conamic.basematerials.tw@heraeus.com

[www.heraeus-conamic.com](http://www.heraeus-conamic.com)